

CreatorDigital Vol

Technical specifications

Property	Test Method	Unit	Tolerance	100	115	130	135	150	170	200	250	300
Substance	ISO 536 TAPPI T410	g/m ²	±4%	100	115	120	135	150	170	200	250	300
Thickness	ISO 534 TAPPI T411	µm	±4%	104	123	128	147	156	182	210	265	327
Opacity	ISO 2471 TAPPI T519	%	-2.0	92.0	93.5	96.0	96.5	97.0	98.0	-	-	-
Whiteness D65/10°	ISO 11475	-	±3	121.4	121.4	121.4	121.4	121.4	121.4	121.4	121.4	121.4
Bekk smoothness	ISO 5627 TAPPI T479	s	≤0.8*STD	-	-	-	100	100	100	100	100	90
Bendtsen roughness	ISO 8971-2 TAPPI UM-535	ML/min	≤1.2*STD	100	100	100	-	-	-	-	-	-
Relative humidity	TAPPI T502	%	±7	48	48	48	48	48	48	48	48	48

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23 °C (±2) de temperature.

In any case, extremes of temperature and humidity must be avoided.

For food contact applications, the product properties, according to the specifications, are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 06/18/2018