Papeterie de Mandeure

Version 2 du 24.02.2020



Ginkgo®

Premium Green Card

Bio material specifically developed for gift card production

Features :

- Comparable stiffness and rigidity to PVC
- Printability in offset, flexo, litho
- Ram punch, die-cut, snapp-off cut
- Magnetic stripe, DOD barcode, Scratch panel
- 100% wood free ECF bleached pulp
- 100% FSC certified pulp
- 100% recyclable
- 100% biodegradable
- 100% compostable EN 13432

Applications :

- Gift cards
- Loyalty cards
- Member cards
- Badges

PRODUCT DATA SHEET

Ginkgo® 600

Material properties:

	Standard	Unit	Tolerance	
Thickness	ISO 534	µm	+/- 15	**600**
Basic Weight	ISO 536	g/m²	+/- 15	**660**
Bendtsen smoothness	TAPPI UM535	ml/m	+/- 25	**70**
Moisture	ISO 287	%	+/- 0.5	**6.5**
Brigthness	TAPPI 452			**113**
Whiteness	CIE			**161**
Internal Scott Bond	NF-03-046	kPa		**5**
Cobb 60'	TAPPI 441	g		**30**
Stiffness MD 15°	TAPPI 489	Taber unit		**550**
Stiffness CD 15°	TAPPI 489	Taber unit		**360**
Stiffness MD	KODAK	Nm		**120**
Stiffness CD	KODAK	Nm		**75**

Papeterie de Mandeure 14 Rue de la Papeterie F-25350 Mandeure Tel. +33 (0)3 81 35 20 52 Fax :+33 (0)3 81 35 30 07 commercial@mandeure.com

Papeterie de Mandeure

Version 2 du 24.02.2020



Ginkgo®

Premium Green Card

Bio material specifically developed for gift card production

Features :

- Comparable stiffness and rigidity to PVC
- Printability in offset, flexo, litho
- Ram punch, die-cut, snapp-off cut
- Magnetic stripe, DOD barcode, Scratch panel
- 100% wood free ECF bleached pulp
- 100% FSC certified pulp
- 100% recyclable
- 100% biodegradable
- 100% compostable EN 13432

Applications :

- Gift cards
- Loyalty cards
- Member cards
- Badges

PRODUCT DATA SHEET

Ginkgo® 700

Material properties:

	Standard	Unit	Tolerance	
Thickness	ISO 534	µm	+/- 15	**700**
Basic Weight	ISO 536	g/m²	+/- 20	**770**
Bendtsen smoothness	TAPPI UM535	ml/m	+/- 25	**70**
Moisture	ISO 287	%	+/- 0.5	**6.5**
Brigthness	TAPPI 452			**113**
Whiteness	CIE			**161**
Internal Scott Bond	NF-03-046	kPa		**4**
Cobb 60'	TAPPI 441	g		**30**
Stiffness MD 15°	TAPPI 489	Taber unit		**850**
Stiffness CD 15°	TAPPI 489	Taber unit		**550**
Stiffness MD	KODAK	Nm		**180**
Stiffness CD	KODAK	Nm		**120**

Papeterie de Mandeure 14 Rue de la Papeterie F-25350 Mandeure Tel. +33 (0)3 81 35 20 52 Fax :+33 (0)3 81 35 30 07 commercial@mandeure.com

Papeterie de Mandeure

Version 2 du 24.02.2020



Ginkgo®

Premium Green Card

Bio material specifically developed for gift card production

Features :

- Comparable stiffness and rigidity to PVC
- Printability in offset, flexo, litho
- Ram punch, die-cut, snapp-off cut
- Magnetic stripe, DOD barcode, Scratch panel
- 100% wood free ECF bleached pulp
- 100% FSC certified pulp
- 100% recyclable
- 100% biodegradable
- 100% compostable EN 13432

Applications :

- Gift cards
- Loyalty cards
- Member cards
- Badges

PRODUCT DATA SHEET

Ginkgo® 750

Material properties:

	Standard	Unit	Tolerance	
Thickness	ISO 534	µm	+/- 15	**740**
Basic Weight	ISO 536	g/m²	+/- 20	**800**
Bendtsen smoothness	TAPPI UM535	ml/m	+/- 25	**70**
Moisture	ISO 287	%	+/- 0.5	**6.5**
Brigthness	TAPPI 452			**113**
Whiteness	CIE			**161**
Internal Scott Bond	NF-03-046	kPa		**4**
Cobb 60'	TAPPI 441	g	maxi	**30**
Stiffness MD 15°	TAPPI 489	Taber unit		**900**
Stiffness CD 15°	TAPPI 489	Taber unit		**630**
Stiffness MD	KODAK	Nm		**210**
Stiffness CD	KODAK	Nm		**140**

Papeterie de Mandeure 14 Rue de la Papeterie F-25350 Mandeure Tel. +33 (0)3 81 35 20 52 Fax :+33 (0)3 81 35 30 07 commercial@mandeure.com